


## Binary FIB Pressure Sensitive Paint

(Product ID: BF-XXX)


Binary FIB pressure sensitive paint (PSP) is a dual-luminophore, single application PSP formulated to be applied with paint spraying equipment. The binary paint approach involves acquiring data from two distinct luminescent dyes and using these signals to compensate for errors caused by model displacement and deformation as well as temperature. One dye is pressure and temperature sensitive and the other dye is temperature sensitive only. The ratio of the signals from the two dyes allows the temperature sensitive signal to be isolated from the pressure sensitive signal. The temperature sensitivity of the paint can be minimized over a wide range of temperatures and pressures as shown in the calibration below. The paint may be applied to most materials, however a white base coat such as SCR-XXX (Screen layer) or FB-XXX (FIB basecoat) is recommended. Models constructed of materials that may be attacked by solvents such as plastic or rapid prototyping resin should be coated with a screen layer or FIB basecoat. The calibration of Binary FIB is very stable, repeatable, and exhibits very little temperature sensitivity. Binary FIB is recommended for advanced/professional PSP users who seek high quality data in low-speed environments or where temperature gradients are larger and have a greater impact on the signal-to noise ratio.




Binary FIB painted on a wing during a transonic test

### SPECIFICATIONS

- Pressure sensitivity ..... 0.6% per kPa
- Pressure range..... 0-kPa to 200-kPa
- Temperature sensitivity ..... 0.03% per °C
- Temperature range..... 0°C to 50°C
- Response time..... 300-ms
- Excitation..... 380-nm to 420-nm
- Emission ..... 500-nm to 720-nm
- Photo-degradation rate..... 1% per hour
- Shelf life ..... 12-months
- ECCN ..... EAR99



Calibration of Binary FIB PSP



Emission spectra of Binary FIB PSP. Paint excited using LM2X-DM-400 LED

Innovative Scientific Solutions, Inc.  
7610 McEwen Road, Dayton, OH 45459  
Phone (937) 630-3012 Fax (937) 630-3015

email: [spalluconi@innsi.com](mailto:spalluconi@innsi.com)  
web: [www.psp-tsp.com](http://www.psp-tsp.com)

Any and all underlying information and technology contained in this document may be subject to U.S. export controls, including the Export Administration Act (50 U.S.C. Appx. §§ 2401 et seq.) and the Export Administration Regulations ("EAR", 50 C.F.R. Parts 730-774), and may be subject to export or import regulations in other countries. You are responsible for complying with all trade regulations and laws both foreign and domestic. Except as authorized by law or distributor agreement with ISSI, you agree and warrant not to export or re-export the information to any country, or to any person, entity, or end-user subject to U.S. export controls, including without limitation persons or entities listed on the U.S. Department of Commerce Bureau of Export Administration's Denied Parties List and the U.S. Department of Treasury's Specially Designated Nationals. You further represent and warrant that no U.S. federal agency has suspended, revoked, or denied your export privileges.